

OK Autrod 430LNb

A continuous ferritic stainless solid wire with low carbon content, 18 % Cr and stabilized with Nb, for welding similar and matching steels. OK Autrod 430LNb is developed and designed for the Automotive industry and used for production of exhaust systems. The wire should be used when there is a need for good resistance to corrosion and thermal fatigue.

Specifiche	
Classificazioni	EN ISO 14343-A : G 18 L Nb Werkstoffnummer : ~1.4511
Omologazioni	CE : EN 13479 UKCA : EN 13479

Le approvazioni si basano sulla posizione della fabbrica. Si prega di contattare ESAB per ulteriori informazioni.

Tipo di lega	18 % Cr - 0.5 % Nb
Gas di protezione	M12, M13 (EN ISO 14175)

Proprietà tensili tipiche			
Stato	Resistenza allo snervamento	Resistenza alla trazione	Allungamento
Come saldato	275 MPa	420 MPa	26 %

analisi tipica del deposito									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.015	0.50	0.50	0.003	0.015	0.2	18.5	0.06	0.10	0.01

analisi tipica del deposito	
Nb	
0.45	

Typical Wire Composition %							
C	Mn	Si	Ni	Cr	Mo	Cu	Nb
0.01	0.5	0.5	0.2	18.5	0.06	0.10	0.45

Dati deposito				
Diametro	Amp	Volt	Velocità di trascinamento del filo	Tasso di deposito
0.8 mm	50-140 A	16-22 V	3.4-11.0 m/min	0.8-2.7 kg/h
1.0 mm	80-190 A	16-24 V	2.9-8.4 m/min	1.1-3.1 kg/h
1.2 mm	180-280 A	20-28 V	4.9-8.5 m/min	2.6-4.5 kg/h

Parametri di saldatura	
Diametro del filo	
0.9 mm	
1.14 mm	