

Exaton 20.25.5.LCuR

Exaton 20.25.5.LCuR is a covered electrode with type with rutile-basic coating and normal recovery, used for welding of high-alloy austenitic stainless of UNS N08904 type, also known as 904L (e.g. Alleima 2RK65). Exaton 20.25.5.LCuR gives a fully austenitic chromium-nickel-molybdenum weld metal with especially low carbon content and copper addition. Spray transfer gives a bead with a finely rippled surface, little spatter and good slag removal. It is suitable for joining steels of the 20Cr/25Ni/4.5Mo/1.5Cu type such as 904L (e.g. Alleima 2RK65) used in many areas of the process industry, such as in the production of acetic acid, sulphuric acid, terephthalic or tartaric acid and vinyl chloride as well as other chloride containing media. It is also suitable for use in cooling operations involving sea water or heavily polluted river water. Exaton 20.25.5.LCuR may also be used to join 317L where improved corrosion resistance in specific media is required. These electrodes may be used to join Alleima 2RK65, 904L and 317L to other grades of stainless steel.

Specifiche	
Classificazioni	EN ISO 3581-A : E 20 25 5 Cu N L R 3 2 SFA/AWS A5.4 : E385-16 Werkstoffnummer : 1.4519
Omologazioni	CE : EN 13479 VdTÜV : 02805

Le approvazioni si basano sulla posizione della fabbrica. Si prega di contattare ESAB per ulteriori informazioni.

Corrente di saldatura	AC, DC+
Contenuto di ferrite	FN 0
Tipo di lega	Austenitic CrNiMo
Tipo di rivestimento	Basic Rutile

Proprietà tensili tipiche			
Stato	Resistenza allo snervamento	Resistenza alla trazione	Allungamento
ISO			
Come saldato	410 MPa	590 MPa	35 %

Proprietà prova Charpy con intaglio a V		
Stato	Temperatura di prova	Valore tenacità
ISO		
Come saldato	20 °C	65 J

analisi tipica del deposito									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.03	1	0.5	0.005	0.019	25	20	4.7	1.5	0.10

analisi tipica del deposito	
FN WRC-92	PREN
0	36

Dati deposito					
Diametro	Amp	Volt	Efficienza (%)	Tempo di fusione per elettrodo al 90% I max	Tasso di deposito al 90% I max
2.5 x 300.0 mm	60-85 A	24 V	60 %	44 sec	0.9 kg/h
3.2 x 350.0 mm	85-130 A	27 V	58 %	60 sec	1.5 kg/h
4.0 x 350.0 mm	95-180 A	29 V	51 %	64 sec	1.9 kg/h