

Exaton 49S

Exaton 49S is a basic, agglomerated flux for electrosag strip surfacing. This flux is particularly intended for high-speed welding. In spite of high welding speed, flux Exaton 49S gives excellent slag removal and bead appearance, also for niobium-alloyed strip electrodes. It is used together with strip electrodes of the chromium, chromium-nickel and chromium-nickel-molybdenum steel types with or without niobium. Exaton 49S gives the following typical chemical properties of all-weld metal for the strip electrode below. Exaton 24.13.LNb is used for corrosion resistant weld surfacing of components in the chemical, petrochemical, nuclear industry. Typical components are pressure vessels, heat exchangers, shafts, industrial piping etc.

Specifiche	
Classificazioni	EN ISO 14174 : ES A FB 2B
Corrente di saldatura	2200 A (Using 60x0.5 mm strip)
Tipo di scoria	Fluoride basic CaF ₂ -Al ₂ O ₃
Densit	nom: 1.0 Kg/l
Indice di basicit	nom: 4.4

Classificazioni	
filo	SFA/AWS - EN ISO
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb
Exaton 21.11.LNb	A5.9:EQ?309LNb?/ 14343-A:B 22 11 L Nb
Exaton 22.11.L	A5.9:EQ(309L)/ 14343-A:B 22 11 L
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb

Approvazioni	
filo	
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.	

analisi tipica del deposito									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L Layer 1 with "24.13.L"									
<=0.03	-	-	-	-	12.0	17.7	2.2	-	-
Exaton 19.13.4.L Layer 1 with "24.13.L"									
<=0.03	-	-	-	-	13.0	18.5	2.7	-	-
Exaton 19.9.L Layer 1 with "24.13.L"									
<=0.03	-	-	-	-	10	19.2	-	-	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb" & Layer 2 with "19.9.LNb")									
0.02	1.4	0.3	-	-	10.5	19.6	0.1	-	0.03
Exaton 19.9.LNb									
-	-	-	-	-	-	-	-	-	-
Exaton 19.9.LNb (Layer 1 with "24.13.L" & Layer 2 with "19.9.LNb")									
0.02	1.3	0.3	-	-	10.6	19.5	0.1	-	0.03
Exaton 21.11.LNb									
-	-	-	-	-	-	-	-	-	-
Exaton 21.11.LNb (1 layer)									
0.02	1.4	0.4	-	-	9.7	18.9	0.1	-	0.05
Exaton 24.13.L									
<=0.07	-	-	-	-	10.2	19	-	-	-
Exaton 24.13.LNb									

Exaton 49S

analisi tipica del deposito

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.06	-	-	-	-	9.7	18.5	-	-	-

analisi tipica del deposito

Nb	FN WRC-92
Exaton 19.12.3.L Layer 1 with "24.13.L"	
-	6
Exaton 19.13.4.L Layer 1 with "24.13.L"	
-	6
Exaton 19.9.L Layer 1 with "24.13.L"	
-	8
Exaton 19.9.LNb (Layer 1 with "24.13.LNb" & Layer 2 with "19.9.LNb")	
0.4	-
Exaton 19.9.LNb (Layer 1 with "24.13.L" & Layer 2 with "19.9.LNb")	
0.3	-
Exaton 21.11.LNb (1 layer)	
0.5	-
Exaton 24.13.L	
-	6
Exaton 24.13.LNb	
-	5

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 21.11.LNb									
<=0.015	1.8	0.2	<=0.020	<=0.020	11	21	<=0.3	<=0.3	-
Exaton 22.11.L									
<=0.015	1.8	0.2	<=0.020	<=0.020	11.5	21	<=0.3	<=0.1	-
Exaton 24.13.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-

Typical Wire Composition %

Nb	Ferrite FN	FN WRC-92
Exaton 19.12.3.L		
-	-	8
Exaton 19.13.4.L		
-	-	7
Exaton 19.9.L		

Exaton 49S

Typical Wire Composition %

Nb	Ferrite FN	FN WRC-92
-	-	12
Exaton 19.9.LNb		
0.5	-	11
Exaton 21.11.LNb		
0.55	-	14
Exaton 22.11.L		
-	13	-
Exaton 24.13.L		
-	-	15
Exaton 24.13.LNb		
0.75	-	22