

Exaton 10SW

Exaton 10SW is a chromium-compensating agglomerated flux giving good slag removal and a fine bead appearance. It is suitable for welding with wire and strip electrodes of the chromium & chromium-nickel and chromium-nickel-molybdenum steel types either with or without niobium. Exaton 10SW is an all round flux which can be used for many applications varying from surfacing continuous caster rolls to large components in chemical plants.

Specifiche	
Classificazioni	EN ISO 14174 : S A CS 2 Cr

Corrente di saldatura	1200 A (Using 60x0.5 mm strip)
Tipo di scoria	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Densit	nom: 1.0 kg/l
Indice di basicit	nom: 1.0

Consumo di Flusso	
Volt	kg flusso/ kg filo DC+
34 V	0.7 kg
30 V	0.55 kg
26 V	0.4 kg
38 V	0.9 kg

Stato : Dimension 4.0 mm , Amp 580 A , Velocit di avanzamento 33 m/h

Classificazioni		
filo	SFA/AWS - EN ISO	AWS-come saldato
Exaton 19.12.3.L	A5.9:ER316L/ 14343-A:S 19 12 3 L	A5.39: F80A10-ER316L/316L
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L	-
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L	-
Exaton 19.9.L	A5.9:ER308L/ 14343-A:S 19 9 L	-
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L	-
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb	-
Exaton 19.9.Nb	A5.9:ER347/ 14343-A:S 19 9 Nb	-
Exaton 21.13.3.L	A5.9:EQ(309LMo)/ 14343-A:B 21 13 3 L	-
Exaton 22.8.3.L	A5.9:EQ2209/ 14343-A:B 22 9 3 N L	-
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L	-
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb	-

Approvazioni	
filo	VdTÜV
Exaton 19.9.L	•
Exaton 19.9.LNb	•
Exaton 19.9.Nb	•
Exaton 22.8.3.L	•

analisi tipica del deposito									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")									
0.02	0.8	0.7	-	-	11.5	19.0	2.2	-	0.06
Exaton 19.13.4.L Layer 1 with "21.13.3.L"									
<=0.04	-	-	-	-	13	18.5	3.3	-	-
Exaton 19.9.L 1st layer with "24.13.L"									
<=0.03	-	-	-	-	10.0	19.7	-	-	-

Exaton 10SW

analisi tipica del deposito									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")									
0.02	0.8	0.6	-	-	10.4	21.0	0.0	-	0.05
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"									
0.04	0.6	1.0	0.01	0.01	9.2	19.0	0.01	0.1	0.06
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"									
<=0.03	-	-	-	-	8.5	22.7	2.9	-	0.16
Exaton 24.13.L Layer 1 with "24.13.L"									
<=0.07	-	-	-	-	10.5	19.2	-	-	-
Exaton 24.13.LNb									
<=0.06	-	-	-	-	9.7	19.2	-	-	-

analisi tipica del deposito		
Nb	FN WRC-92	Nb+Ta
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")		
0	-	-
Exaton 19.13.4.L Layer 1 with "21.13.3.L"		
-	5	-
Exaton 19.9.L 1st layer with "24.13.L"		
-	8	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")		
0.3	-	-
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"		
0.3	-	0.3
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"		
-	40	-
Exaton 24.13.L Layer 1 with "24.13.L"		
-	6	-
Exaton 24.13.LNb		
-	6	-

Typical Wire Composition %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 19.9.Nb									
0.04	1.3	0.35	0.012	0.015	9.5	19.5	0.03	0.11	0.06
Exaton 21.13.3.L									
<=0.015	1.8	0.2	<=0.015	<=0.020	13.5	20.5	2.9	<=0.3	-
Exaton 22.8.3.L									
<=0.020	1.6	0.5	<=0.015	<=0.020	9	23	3.1	-	0.15
Exaton 24.13.L									

Exaton 10SW

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-

Typical Wire Composition %

Nb	Co	FN deLong	FN WRC	FN WRC-92	Nb+Ta
Exaton 19.12.3.L					
-	-	-	-	8	-
Exaton 19.13.4.L					
-	-	-	-	7	-
Exaton 19.9.L					
-	-	-	-	12	-
Exaton 19.9.LNb					
0.5	-	-	-	11	-
Exaton 19.9.Nb					
0.6	0.1	5	5	-	0.6
Exaton 21.13.3.L					
-	-	-	-	13	-
Exaton 22.8.3.L					
-	-	-	-	50	-
Exaton 24.13.L					
-	-	-	-	15	-
Exaton 24.13.LNb					
0.75	-	-	-	22	-

Propriet  meccaniche tipiche

filo	Stato	Resistenza allo snervamento	Resistenza alla trazione	Allungamento	Intaglio a V Charpy
Exaton 19.12.3.L	Come saldato	420 MPa	580 MPa	32 %	69 J @ 20 �C 60 J @ -40 �C 55 J @ -70 �C 50 J @ -196 �C
Exaton 19.9.L	Come saldato	400 MPa	580 MPa	38 %	69 J @ 20 �C 59 J @ -40 �C 40 J @ -196 �C
Exaton 19.9.Nb	Come saldato Joining	440 MPa	625 MPa	38 %	72 J @ 20 �C 61 J @ -40 �C 34 J @ -196 �C