

Exaton 31S

31S is a neutral welding flux for submerged arc welding giving good slag removal and fine bead appearance. It is suitable for surfacing with strip and wire electrodes and can also be used for joining. 31S is intended primarily for welding with strip or wire electrodes of the 310LMo type such as 25.22.2.LMn for urea applications.

Specifications

Classifications	EN ISO 14174 : S A AB 2
------------------------	-------------------------

Welding Current	1200
Density	nom: 0.9 Kg/l
Basicity Index	nom: 1.0

Classifications_SAW

Wire	AWS/EN
Exaton 25.22.2.LMn	14343-A:B 25 22 2 N L
Exaton 25.22.2.LMn	14343-A:S 25 22 2 N L

Approvals_SAW

Wire

*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	N
Exaton 25.22.2.LMn								
0.02	3.8	0.6	-	-	22	24.5	2	0.12

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 25.22.2.LMn									
<=0.020	4.5	<=0.2	<=0.015	<=0.015	22.0	25.0	2.1	0.05	0.13

Typical Wire Composition %

FN WRC-92

Exaton 25.22.2.LMn

0

SAW_Typical_Mech_Properties

Wire	Testing Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch Result
Exaton 25.22.2.LMn	As Welded	380 MPa	570 MPa	40 %	75 J @ 20 °C 40 J @ -196 °C
Exaton 25.22.2.LMn	As Welded	320 MPa	560 MPa	50 %	65 J @ -196 °C