

OK 67.50

OK 67.50 is an acid rutile coated type for welding of austenitic-ferritic stainless steels of CrNiMoN 22 5 3 - and CrNiN 23 4-types. The duplex all weld metal offers a high strength level combined with good ductility. The pitting corrosion resistance is good and the all weld metal is not sensitive for stress corrosion cracking.

Specifications	
Classifications	EN ISO 3581-A : E 22 9 3 N L R 3 2 SFA/AWS A5.4 : E2209-17 CSA W48 : E2209-17 Werkstoffnummer : 1.4462
Approvals	ABS : E2209-17 ABS : Stainless* BV : 2209 CE : EN 13479 CWB : E2209-17 DNV-GL : Duplex RINA : 2209 UKCA : EN 13479 VdTÜV : 04368

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+, AC
Ferrite Content	FN 35-50
Alloy Type	Duplex CrNiMoN
Coating Type	Acid Rutile

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
ISO			
As Welded	691 MPa	857 MPa	25 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
ISO		
As Welded	20 °C	50 J
As Welded	-30 °C	41 J

Typical Weld Metal Analysis %							
C	Mn	Si	Ni	Cr	Mo	N	FN WRC-92
0.03	0.8	0.8	8.8	23.2	3.2	0.16	42

Deposition Data					
Diameter	Current	Voltage	Efficiency (%)	Fusion time per electrode at 90% I max	Deposition Rate
2.0 x 300.0 mm	30-65 A	29 V	55 %	33 sec	0.7 kg/h
2.5 x 300.0 mm	50-90 A	27 V	58 %	38 sec	1.0 kg/h
3.2 x 350.0 mm	80-120 A	28 V	58 %	55 sec	1.4 kg/h
4.0 x 350.0 mm	90-160 A	29 V	58 %	59 sec	1.9 kg/h
5.0 x 350.0 mm	150-220 A	30 V	58 %	64 sec	2.8 kg/h