

OK Tigrod 19.92

A bare nickel based rod alloyed with about 3% Ti for welding of high purity nickel (min 99,6 % Ni), ordinary wrought nickel and nickel with reduced C content. The weld metal can be used in a wide range of applications where the construction is working with corrosive media.

Specifications

Classifications	SFA/AWS A5.14 : ERNi-1 EN ISO 18274 : S Ni 2061 (NiTi3)
Approvals	VdTÜV : 02787 (MV) VdTÜV : 06280 (FP)

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Nickel (Ni + 2.5 % Ti)
-------------------	------------------------

Typical Charpy V-Notch Properties

Condition	Testing Temperature
As Welded	20 °C