

OK Autrod 409Nb

A ferritic stabilized stainless solid welding wire of 12% Cr and 0,4% Nb type. OK Autrod 409Nb is used for welding of similar steels in applications such as catalytic converters and mufflers.

Specifications

Classifications	SFA/AWS A5.9 : ER409Nb
Alloy Type	Ferritic stainless (12 % Cr - 0.4 % Nb)
Shielding Gas	M11, M12, M21 (EN ISO 14175)

Typical Wire Composition %

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.0 mm	80-190 A	16-24 V	2.9-8.4 m/min	1.1-3.1 kg/h
1.2 mm	180-280 A	20-28 V	4.9-8.5 m/min	2.6-4.5 kg/h