

## OK 94.25

Electrode for welding copper and bronzes, especially tin-bronzes. It is also suitable for cladding steels and for smaller repair work of weldable cast irons.

### Specifications

<b>Classifications</b>	EN ISO 17777 : E Cu Z (CuSn7)
------------------------	-------------------------------

<b>Welding Current</b>	DC+
<b>Alloy Type</b>	Copper alloy
<b>Coating Type</b>	Basic

### Tensile Properties

Testing Condition	Yield Strength	Tensile Strength	Elongation
<b>ISO</b>			
As Welded	235 MPa	360 MPa	25 %

### Charpy Testing

Testing Condition	Testing Temp	Impact Value
<b>ISO</b>		
As Welded	20 °C	25 J
As Welded	0 °C	20 J

### Typical Weld Metal Analysis %

Mn	Cu	Sn
0.4	93	6.5

### Deposition Data

Diameter	Amps	Volts	Efficiency (Per)	Fusion time per electrode at 90Per I max	Deposition rate at 90Per
2.5 x 350.0 mm	60-90 A	22 V	71 %	39 sec	1.2 kg/h
3.2 x 350.0 mm	90-125 A	24 V	72 %	40 sec	1.9 kg/h
4.0 x 350.0 mm	125-170 A	25 V	74 %	41 sec	2.9 kg/h