

OK Autrod 12.10

Copper-coated, unalloyed wire for Submerged Arc Welding. For low requirements or in combination with high Si and Mn alloying fluxes. Suitable for non- and low alloyed steels.

Specifications	
Classifications	SFA/AWS A5.17 : EL12 EN ISO 14171-A : S1
Approvals	CE : EN 13479 DB : 52.039.01 UKCA : EN 13479 VdTÜV : 12103

Approvals are based on factory location. Please contact ESAB for more information.

Typical Wire Composition %		
C	Mn	Si
0.07	0.52	0.08