

OK Tigrod 13.08

A copper coated, low alloyed, manganese-molybdenum (1,5% Mn, 0,4% Mo) rod for GTAW of creep resistant steels of the same type, such as pipes in pressure vessels and boilers with a working temperature of up to about 500°C. The rod can also be used for welding low-alloyed high tensile strength steels.

Specifications

Classifications	EN ISO 636-A : W 50 3 Z 2Mo
	EN ISO 636-B : W55A 3 4M31
	EN ISO 636-A : Z 2Mo
	EN ISO 636-B : 4M31
	SFA/AWS A5.28 : ER80S-D2

Approvals	NAKS/HAKC : 2.4MM
------------------	-------------------

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Low alloyed steel (0.5 % Mo)
-------------------	------------------------------

Shielding Gas	I1 (EN ISO 14175)
----------------------	-------------------

Tensile Properties

Testing Condition	Yield Strength	Tensile Strength	Elongation
Ar (I1) AWS			
As Welded	520 MPa	615 MPa	28 %
Ar (I1) EN			
As Welded	620 MPa	690 MPa	24 %

Charpy Testing

Testing Condition	Testing Temp	Impact Value
Ar (I1) AWS		
As Welded	-30 °C	80 J
Ar (I1) EN		
As Welded	-30 °C	110 J

Typical Wire Composition %

C	Mn	Si	Ni	Mo
0.07	1.8	0.7	0.05	0.4