

ALUMINIO

ALAMBRES SOLIDOS Y VARILLAS (GMAW/GTAW)

ALTIGWELD 5556

Alloy 5556 was first utilized in 1956. It develops the highest as-Welded strengths in fillet welds and it is nearly double that of 4043. The 5Xxx eries of Alloys offer an excellent combination of Corrosion Resistance, Strength, Toughness, Workability, and Weldability. As a result, they are used in a wide variey of applications. A characteristic of this series of Alloys. However, is their Susceptibility to stress corrosion cracking when the weld pool chemistry is greater than 3% Mg and there is exposure to prolonged temperatures in excess of 150° F. Special Alloys and Tempers are often required to overcome this problem. Contact Alcotec for assistance in Alloy/Temper selection.

Especificaciones	
Clasificaciones	ANSI/AWS A5.10 : (ER & R)
Aprobaciones	ABS : R 5556 ClassNK CWB DNV KR LR

Las aprobaciones se basan en la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

tipo de aleación	Aluminum
------------------	----------

% típico de composición de alambre							
Mn	Si	Cr	Cu	Ti	Zn	Fe	Mg
0.7	0.5	0.10	0.01	0.080	0.005	0.12	5.2