

Exaton 10SW

Exaton 10SW is a chromium-compensating agglomerated flux giving good slag removal and a fine bead appearance. It is suitable for welding with wire and strip electrodes of the chromium & chromium-nickel and chromium-nickel-molybdenum steel types either with or without niobium. Exaton 10SW is an all round flux which can be used for many applications varying from surfacing continuous caster rolls to large components in chemical plants.

Specificaties

Classificaties	EN ISO 14174 : S A CS 2 Cr
Lasstroom	1200 A (Using 60x0.5 mm strip)
Slaktype	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Dichtheid	nom: 1.0 kg/l
Basiciteits Index	nom: 1.0

Fluxverbruik

Volt	kg Flux / kg Draad DC+
34 V	0.7 kg
30 V	0.55 kg
26 V	0.4 kg
38 V	0.9 kg

Conditionering : Afmeting 4.0 mm , Ampère 580 A , Voortloopsnelheid 33 m/h

Normen

Draad	AWS/EN	AWS - Als gelaste
Exaton 19.12.3.L	A5.9:ER316L/ 14343-A:S 19 12 3 L	A5.39: F80A10-ER316L/316L
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L	-
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L	-
Exaton 19.9.L	A5.9:ER308L/ 14343-A:S 19 9 L	-
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L	-
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb	-
Exaton 19.9.Nb	A5.9:ER347/ 14343-A:S 19 9 Nb	-
Exaton 21.13.3.L	A5.9:EQ(309LMo)/ 14343-A:B 21 13 3 L	-
Exaton 22.8.3.L	A5.9:EQ2209/ 14343-A:B 22 9 3 N L	-
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L	-
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb	-

Goedkeuringen

Draad	VdTÜV
Exaton 19.9.L	•
Exaton 19.9.LNb	•
Exaton 19.9.Nb	•
Exaton 22.8.3.L	•

draad samenstelling

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-

Exaton 10SW

draad samenstelling									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 19.9.Nb									
0.04	1.3	0.35	0.012	0.015	9.5	19.5	0.03	0.11	0.06
Exaton 21.13.3.L									
<=0.015	1.8	0.2	<=0.015	<=0.020	13.5	20.5	2.9	<=0.3	-
Exaton 22.8.3.L									
<=0.020	1.6	0.5	<=0.015	<=0.020	9	23	3.1	-	0.15
Exaton 24.13.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-

draad samenstelling					
Nb	Co	FN deLong	FN WRC	FN WRC-92	Nb+Ta
Exaton 19.12.3.L					
-	-	-	-	8	-
Exaton 19.13.4.L					
-	-	-	-	7	-
Exaton 19.9.L					
-	-	-	-	12	-
Exaton 19.9.LNb					
0.5	-	-	-	11	-
Exaton 19.9.Nb					
0.6	0.1	5	5	-	0.6
Exaton 21.13.3.L					
-	-	-	-	13	-
Exaton 22.8.3.L					
-	-	-	-	50	-
Exaton 24.13.L					
-	-	-	-	15	-
Exaton 24.13.LNb					
0.75	-	-	-	22	-

Typische lasmetaalanalyse (%)									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")									
0.02	0.8	0.7	-	-	11.5	19.0	2.2	-	0.06
Exaton 19.13.4.L Layer 1 with "21.13.3.L"									
<=0.04	-	-	-	-	13	18.5	3.3	-	-
Exaton 19.9.L 1st layer with "24.13.L"									
<=0.03	-	-	-	-	10.0	19.7	-	-	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")									
0.02	0.8	0.6	-	-	10.4	21.0	0.0	-	0.05
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"									
0.04	0.6	1.0	0.01	0.01	9.2	19.0	0.01	0.1	0.06
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"									

Exaton 10SW

Typische lasmetaalanalyse (%)

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.03	-	-	-	-	8.5	22.7	2.9	-	0.16
Exaton 24.13.L Layer 1 with "24.13.L"									
<=0.07	-	-	-	-	10.5	19.2	-	-	-
Exaton 24.13.LNb									
<=0.06	-	-	-	-	9.7	19.2	-	-	-

Typische lasmetaalanalyse (%)

Nb	FN WRC-92	Nb+Ta
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")		
0	-	-
Exaton 19.13.4.L Layer 1 with "21.13.3.L"		
-	5	-
Exaton 19.9.L 1st layer with "24.13.L"		
-	8	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")		
0.3	-	-
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"		
0.3	-	0.3
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"		
-	40	-
Exaton 24.13.L Layer 1 with "24.13.L"		
-	6	-
Exaton 24.13.LNb		
-	6	-

Typische mechanische eigenschappen

Draad	Conditionering	Rekgrens	Treksterkte	Rek	Charpy V-groef
Exaton 19.12.3.L	Zoals gelast	420 MPa	580 MPa	32 %	69 J @ 20 °C 60 J @ -40 °C 55 J @ -70 °C 50 J @ -196 °C
Exaton 19.9.L	Zoals gelast	400 MPa	580 MPa	38 %	69 J @ 20 °C 59 J @ -40 °C 40 J @ -196 °C
Exaton 19.9.Nb	Zoals gelast Joining	440 MPa	625 MPa	38 %	72 J @ 20 °C 61 J @ -40 °C 34 J @ -196 °C