

Exaton 25.22.2.LMnB

Exaton 25.22.2.LMnB is a chromium-nickel-molybdenum covered electrode with basic coating for welding of austenitic stainless steels for example, Sandvik 2RE69 and Sandvik 3R60 U.G used in the production of ammonium carbamate, nitric acid and inorganic acids. It is also used for surfacing on low alloyed steels. The electrode combines good welding properties such as arc stability, low spatter and self peeling slag with very low impurity levels. The fully austenitic weld metal (maximum 0.6% ferrite) is very resistant to hot cracking. Exaton 25.22.2.LMn is used for welding of Sandvik 2RE69 and Sandvik 3R60 U.G. urea grade materials. But it can also be used for the following types: ISO 1.4466, 1.4335, 1.4435, 1.4436, 1.4477, 1.4578 and 1.4585; UNS S31050, S31002, S31603 and S31600.

Tekniska data

Klassificeringar	EN ISO 3581-A : E 25 22 2 N L B 12 SFA/AWS A5.4 : (E310Mo-15)
-------------------------	--

Svetsström	DC+
Ferrithalt	FN 0
Legeringstyp	25Cr 22Ni 2Mo N
Höljtyp	Basic

Typiska mekaniska värden

Villkor	Sträckgräns	Brottgräns	Förlängning
ISO			
Helsvetsgods	420 MPa	600 MPa	30 %

Slagseghetsdata Charpy V

Villkor	Provningstemperatur	Slagseghet
ISO		
Helsvetsgods	20 °C	70 J

Svetsgodsanalys %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.04	4.5	0.4	<=0.020	<=0.020	22	25	2.1	0.05	0.14

Svetsgodsanalys %

FN WRC-92
0

Insmålningsdata

Diameter	Ström	Verkningsgrad (%)	Smälttid per elektrod vid 90% av maxström	Insvetstal vid 90 % I max
2.5 x 300.0 mm	60-80 A			0.0 kg/h
3.2 x 350.0 mm	80-110 A	64 %	55 sec	1.7 kg/h
4.0 x 350.0 mm	110-140 A	53 %	75 sec	2.3 kg/h