

Exaton Ni60

Exaton Ni60 is a nickel-chromium-molybdenum covered electrode for welding of Ni/Cr/Mo nickel alloys, highalloy stainless steels and 5-9%Ni steels in cryogenic applications. It can be used in many variants of dissimilar joining of nickel alloys, stainless steels and low alloyed steels. Exaton Ni60 can also be used for overlay welding on low alloyed steels. The electrode combines good welding properties in all positions with very low impurity levels, high impact strength and excellent corrosion resistance to pitting in chloride containing media and stress corrosion cracking. Typical applications for Exaton Ni60 include components in the chemical and petrochemical industries often in connection with sea-water cooling where pitting corrosion and stress corrosion cracking are a risk, pressure vessels, heat exchangers etc. It is also used in sour gas service where it is approved by ISO 15156/NACE MR0175. Common base materials welded are ASTM UNS: S31254, N06625, N08825 and N08020.

Tekniska data

Klassificeringar	SFA/AWS A5.11 : ENiCrMo-3 EN ISO 14172 : E Ni 6625 (NiCr22Mo9Nb)
Godkännanden	VdTÜV : 04796

Godkännanden baseras på fabriksplats. Kontakta ESAB för mer information.

Svetsström	DC+
Legeringstyp	Ni-based CrMoNb
Höljtyp	Basic

Typiska mekaniska värden

Villkor	Sträckgräns	Brottgräns	Förlängning
ISO			
Helsvetsgods	520 MPa	820 MPa	38 %

Slagseghetsdata Charpy V

Villkor	Provningstemperatur	Slagseghet
ISO		
Helsvetsgods	20 °C	70 J
Helsvetsgods	-196 °C	65 J

Svetsgodsanalys %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Nb
0.03	0.23	0.4	<=0.01	<=0.015	63	22	9	0.01	3.4

Svetsgodsanalys %

Others tot	Fe	Nb+Ta
<=0.50	<=2	3.4

Insmålningsdata

Diameter	Ström	Bågspänning	Verkningsgrad (%)	Smälttid per elektrod vid 90% av maxström	Insvetstal vid 90 % I max
2.5 x 300.0 mm	55-75 A	23 V	55 %	40 sec	0.9 kg/h
3.2 x 350.0 mm	65-100 A	25 V	56 %	52 sec	1.4 kg/h
4.0 x 350.0 mm	80-140 A	27 V	58 %	57 sec	1.9 kg/h
5.0 x 350.0 mm	120-170 A	24 V	58 %	72 sec	2.1 kg/h