

Exaton 47S

Exaton 47S is a highly basic welding flux for electroslag strip surfacing. It gives excellent slag removal and bead appearance also for niobium-alloyed strip electrodes. Flux Exaton 47S is used together with strip electrodes of steel types chromium, chromium-nickel and chromium-nickel-molybdenum with or without niobium. The high basicity of flux Exaton 47S makes it especially suitable for duplex, super-duplex and fully austenitic stainless steel surfacings.

Dane techniczne

Klasyfikacje	EN ISO 14174 : ES A FB 2B
Prd spawania	1700 A (Using 60x0.5 strip)
Typ ulu	Fluoride basic CaF ₂ -Al ₂ O ₃
Gsto	nom: 1.0 Kg/l
Wskanik zasadowoci	nom: 4.0

Warunki : V 25 V , Zucie topnika / 1 kg(2,2 lb) drutu DC+ 0.5 kg , A 1250 A , Prdko jazdy 9 m/h

Klasyfikacje

Drut	AWS/EN	AWS - stan po spawaniu
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L	-
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L	-
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L	-
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb	-
Exaton 21.11.LNb	A5.9:EQ?309LNb?/ 14343-A:B 22 11 L Nb	A5.39: ESCLAD1-EQ309L(mod)/347
Exaton 21.13.3.L	A5.9:EQ(309LMo)/ 14343-A:B 21 13 3 L	-
Exaton 22.11.L	A5.9:EQ(309L)/ 14343-A:B 22 11 L	A5.39: ESCLAD1-EQ309L(Mod)/308L
Exaton 22.8.3.L	A5.9:EQ2209/ 14343-A:B 22 9 3 N L	-
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L	-
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb	-
Exaton 25.22.2.LMn	14343-A:B 25 22 2 N L	-

Dopuszczenia

Drut
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.

Skad drutu %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 21.11.LNb									
<=0.015	1.8	0.2	<=0.020	<=0.020	11	21	<=0.3	<=0.3	-
Exaton 21.13.3.L									
<=0.015	1.8	0.2	<=0.015	<=0.020	13.5	20.5	2.9	<=0.3	-
Exaton 22.11.L									
<=0.015	1.8	0.2	<=0.020	<=0.020	11.5	21	<=0.3	<=0.1	-
Exaton 22.8.3.L									
<=0.020	1.6	0.5	<=0.015	<=0.020	9	23	3.1	-	0.15

Exaton 47S

Skad drutu %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 24.13.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-
Exaton 25.22.2.LMn									
<=0.020	4.5	<=0.2	<=0.015	<=0.015	22.0	25.0	2.1	-	0.13

Skad drutu %	
Nb	FN WRC-92
Exaton 19.12.3.L	
-	8
Exaton 19.13.4.L	
-	7
Exaton 19.9.L	
-	12
Exaton 19.9.LNb	
0.5	11
Exaton 21.11.LNb	
0.55	14
Exaton 21.13.3.L	
-	13
Exaton 22.11.L	
-	13
Exaton 22.8.3.L	
-	50
Exaton 24.13.L	
-	15
Exaton 24.13.LNb	
0.75	22

Typowy skad chemiczny stopiwa %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L 1st layer with "22.11.L"									
<=0.03	-	-	-	-	12	18.2	2.3	-	-
Exaton 19.13.4.L 1st layer with "22.11.L"									
<=0.03	-	-	-	-	13	18.5	3.2	-	-
Exaton 19.13.4.L 1st layer with "21.13.3.L"									
<=0.03	-	-	-	-	13.2	18.5	3.4	-	-
Exaton 19.9.L 1st layer with "22.11.L"									
<=0.030	-	-	-	-	10	19.5	-	-	-
Exaton 19.9.LNb (Layer 1 with "21.11.L" & Layer 2 with "19.9.LNb")									
0.01	1.2	0.4	0.009	0.014	10.5	19.2	0.1	0.06	0.03
Exaton 21.11.LNb (1-layer)									
0.02	1.3	0.5	0.001	0.01	10.1	19.3	0.1	0.03	0.05
Exaton 21.13.3.L (1 layer)									
0.02	1.1	0.4	0.002	0.013	12.5	18.7	2.7	0.06	0.03
Exaton 22.11.L									

Exaton 47S

Typowy skład chemiczny stopiwa %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.06	-	-	-	-	9.7	18.5	-	-	-
Exaton 22.8.3.L Layer 1 with "22.8.3.L" & 2 layers with "22.8.3.L"									
<=0.02	-	-	-	-	8.5	22.5	3.1	-	0.16
Exaton 22.8.3.L Layer 1 with "22.11.L" & 2 layers with "22.8.3.L"									
<=0.02	-	-	-	-	8.5	22.5	3.0	-	0.15
Exaton 24.13.L									
0.03	1.4	0.54	0.003	0.015	10.9	19.0	0.10	0.03	0.04
Exaton 24.13.LNb (1 layer)									
0.03	1.5	0.4	0.002	0.011	10.7	20.8	0.2	0.04	0.04
Exaton 25.22.2.LMn (2 layers)									
0.02	3.5	0.4	0.002	0.016	22.0	24.6	2.0	-	0.14

Typowy skład chemiczny stopiwa %

Nb	FN WRC-92	Nb+Ta
Exaton 19.12.3.L 1st layer with "22.11.L"		
-	6	-
Exaton 19.13.4.L 1st layer with "22.11.L"		
-	6	-
Exaton 19.13.4.L 1st layer with "21.13.3.L"		
-	6	-
Exaton 19.9.L 1st layer with "22.11.L"		
-	8	-
Exaton 19.9.LNb (Layer 1 with "21.11.L" & Layer 2 with "19.9.LNb")		
-	8	0.3
Exaton 21.11.LNb (1-layer)		
0.4	5	-
Exaton 21.13.3.L (1 layer)		
-	8	-
Exaton 22.11.L		
-	6	-
Exaton 22.8.3.L Layer 1 with "22.8.3.L" & 2 layers with "22.8.3.L"		
-	45	-
Exaton 22.8.3.L Layer 1 with "22.11.L" & 2 layers with "22.8.3.L"		
-	45	-
Exaton 24.13.L		
-	3	-
Exaton 24.13.LNb (1 layer)		
-	13	0.6
Exaton 25.22.2.LMn (2 layers)		
-	0	-