

OK Autrod 12.40

Copper-coated, unalloyed wire for Submerged Arc and Electroslag Welding. For structural steels, ship building steels, pressure vessel steels, fine grained steels, etc.

Specifications

Classifications	SFA/AWS A5.17 : EH14
	EN ISO 14171-A : S4
Approvals	VdTÜV : 12103

Approvals are based on factory location. Please contact ESAB for more information.

Typical Wire Composition %

C	Mn	Si
0.12	2.04	0.08