

OK Autrod 13.36 SAW

OK Autrod 13.36 is a C 1.0%Mn, 0.8%Ni, 0.4%Cu wire used in combination with OK Flux 10.71 to weld weather resisting steels used in the construction of buildings, bridges, boilers, exhaust chimneys etc. The weld metal has improved corrosion to that of carbon manganese weld metal when exposed to environments containing salt water, sulphurous gases and caustic liquors.

Specifications

Classifications	EN ISO 14171-A : S2Ni1Cu SFA/AWS A5.23 : EG
------------------------	--

Charpy Testing

Testing Condition	Testing Temp	Impact Value
As Welded	+20 °C	120 J
As Welded	-20 °C	70 J