

OK Tubrodur 15.39

A 2% Cr hardfacing metal cored wire for use with CO2 shielding gas.

Tekniska data

Klassificeringar	EN 14700 : T Fe1 DIN 8555 : MF1-300P
------------------	---

Svetsström	DC+
Legeringstyp	Hardfacing 2% Cr
Skyddsgas	C1 (EN ISO 14175)

Insmålningsdata

Diameter	Ström	Bågspänning	Trådmatningshastighet	Insvetstal
1.6 mm	150-450 A	21-40 V	2.4-11.9 m/min	1.8-9.0 kg/h