

## **OK Autrod NiCrMo-4**

OK Autrod NiCrMo-4 is a corrosion and heat resistant, nickel-chromium wire for submerged arc welding of high alloyed steel, heat resistant steel, corrosion resistant steel, 9Ni steels and similar steels with high notch toughness at low temperatures. OK Autrod NiCrMo-4 can be combined with OK Flux 10.99, OK Flux 10.90 or OK Flux 10.16

Specifications					
Classifications	SFA/AWS A5.14 : ERNiCrMo-4 EN ISO 18274 : S Ni 6276 (NiCr15Mo16Fe6W4)				
Approvals	NAKS/HAKC : 2.4mm				

Approvals are based on factory location. Please contact ESAB for more information.

Typical Wire Composition %									
С	Mn	Si	Ni	Cr	Мо	w	Fe		
0.01	0.45	0.05	Bal.	15.5	16.1	3.5	5.8		