

FILARC PZ6105R

A metal cored wire for robotic welding of single and multi-pass fillet welds using M21 and M12 shielding gas. Used in the downhand and horizontal / vertical positions.

Specifications

Classifications	SFA/AWS A5.18 : E70C-6M H4 EN ISO 17632-A : T 42 4 M M12 3 H5 EN ISO 17632-A : T 42 4 M M21 3 H5
Approvals	ABS : 4Y400SA H5 BV : S3YM H5 CE : EN 13479 DB : 42.105.14 DNV : IV Y40(H5) LR : 4Y40M H5 LR : 4Y40S H5 UKCA : EN 13479 VdTÜV : 09082

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+
Alloy Type	CMn
Shielding Gas	M12, M21 (EN ISO 14175)

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
M21 shielding gas			
As Welded	453 MPa	558 MPa	32 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
M21 shielding gas		
As Welded	-40 °C	55 J

Typical Weld Metal Analysis %

C	Mn	Si
M21 shielding gas		
0.045	1.72	0.76
M12 shielding gas		
0.045	1.8	0.80

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.2 mm	100-350 A	14-32 V	1.8-18.5 m/min	1.3-8.0 kg/h
1.4 mm	150-350 A	18-33 V	3.5-12.1 m/min	2.1-7.2 kg/h
1.6 mm	250-450 A	28-38 V	4.3-10.7 m/min	3.4-8.5 kg/h