

## OK Weartrade 60 T

Electrode giving a weld metal with coarse chromium carbides in an austenitic matrix. Suitable for surfacing worn parts in earth-moving equipment, sand pumps, mixers, feed screws, dust extractors, crushers etc exposed to wear by coal, ores and other minerals. Also in corrosive environment and/or elevated temperature.

### Specifications

<b>Classifications</b>	EN 14700 : E Z Fe14
------------------------	---------------------

<b>Welding Current</b>	AC, DC+
<b>Alloy Type</b>	Carbide rich steel
<b>Coating Type</b>	Rutile Basic

### Typical Weld Metal Analysis %

<b>C</b>	<b>Mn</b>	<b>Si</b>	<b>Cr</b>
4.8	1.0	0.7	34.3

### Deposition Data

Diameter	Amps	Volts	Efficiency (Per)	Fusion time per electrode at 90Per I max	Deposition rate at 90Per
2.5 x 350.0 mm	90-120 A	24 V	62 %	60 sec	1.2 kg/h
3.2 x 350.0 mm	115-170 A	24 V	62 %	85 sec	1.6 kg/h
4.0 x 450.0 mm	130-210 A	26 V	64 %	135 sec	2.0 kg/h
5.0 x 450.0 mm	150-300 A	26 V	64 %	140 sec	2.9 kg/h