

ESAB 7018-1 Prime

ESAB 7018-1 Prime is a reliable, high-quality electrode, providing high deposition rate and extra low moisture absorption. It provides excellent welding pool control, minimal spatter level, good arc strike and easy slag removal making it easy to weld with, including in out-of-position welding. Particularly suitable for welding high strength low-alloy steels. The low-temperature impact strength of the weld metal should be noted.

Specifications	
Classifications	SFA/AWS A5.1 : E7018-1H4 R SFA/AWS A5.1 : E7018H4 R CSA W48 : E4918-1-H4 EN ISO 2560-A : E 46 5 B 32 H5
Approvals	ABS : 3Y H5 BV : 3Y H5 CWB : E4918-1-H4 DNV-GL : 3Y H5

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	AC, DC+
Diffusible Hydrogen	< 4.0 ml/100g
Alloy Type	Carbon Manganese
Coating Type	Basic covering

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
AWS			
As Welded	500 MPa (73 ksi)	590 MPa (86 ksi)	28 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
AWS		
As Welded	-45 °C (-49 °F)	105 J (78 ft-lb)
As Welded	-50 °C (-58 °F)	100 J (74 ft-lb)

Deposition Data					
Diameter	Current	Voltage	Deposition Efficiency (%)	Burn-off Time /Electrode	Deposition Rate @ 90% I max
2.4 x 350.0 mm (3/32 x 13.8 in.)	80-110 A	23 V	64 %	64 sec	0.9 kg/h (2.0 lbs/h)
3.2 x 350.0 mm (1/8 x 13.8 in.)	110-140 A	23 V	62 %	72 sec	1.2 kg/h (2.6 lbs/h)
4.0 x 350.0 mm (5/32 x 13.8 in.)	140-200 A	23 V	62 %	72 sec	1.77 kg/h (3.9 lbs/h)